

#### 4.4 Leather, suede and imitation leather

<b>Compulsory tests</b>			<b>Requirements</b>
	<b>Colour fastness</b>		
ISO 105 - X12 (2002)	Colour fastness to rubbing	M	Dry: 4 Wet: 3-4
ISO 105 - E04 (2002)	Colour fastness to perspiration	M	Colour change: 4 Staining: 3-4
ISO 105 - D01 (2010)	Colour fastness to dry-cleaning	M	Colour change: 4 Staining: 4
ISO 105 – E01 (2002)/ BS 1006 E01	Colour fastness to water	M	Colour change: 4 Staining: 4
ISO 105 B02 (2002)/ BS 1006 B02	Colour fastness to light	M	Grey scale: 4 BSW: 4
<b>Tests on demand</b>			
<b>Mechanical &amp; Physical properties</b>			
ISO13937-1 (2000) Elmendorf	Tear strength	O	25N
<b>For imitation leather</b>			
ISO 2411	Bonding strength	O	Length and width 5N/cm

**M= Mandatory / O= Optional (only on request of Wehkamp)**